



Kai Greising KG  
Clean Marker

[www.greising.com](http://www.greising.com)  
[Info@greising.com](mailto:Info@greising.com)

Industriestr. 29/2  
D-73340 Amstetten

Tel. +49 (0)73 31 - 30 58 0  
Fax +49 (0)73 31 - 98 17 22

Auftragsbearbeitung  
+49(0)73 31 - 30 58 20

Technische Auskünfte  
+49(0)73 31 - 30 58 24  
Ust-ID Nr.221377945

# Technical data sheet

## Pickling Paste Greinox P

**Transparent pickling paste for stainless steel, with increased acid content**

### Field of application

Removal of annealing colours in the area of the welding seams and heat-affected zones.  
A clean metallic surface in the application area is obtained.

### Use

Apply a sufficient amount of pickling paste manually with a special pickling brush to the area that is to be treated.

**Attention:** welding seams and heat-affected zones must be allowed to cool down before using the product.

Read the packing label before use and follow the instructions.

### Yield

Approx. 50-80 m of welding seam per kg **Greinox P** Pickling Paste Extra, dependent on the condition and the dimensions of the welding seam area.

### Residence time

30 – 120 minutes

Dependent on the material quality, welding process, component and ambient temperature.

Optimal pickling temperature: 18°C – 22°C.

### Rinsing

Cold high pressure water (min. 140 bar).

Rinse until rinsing water is neutral (to be checked with indicator paper).

### Subsequent treatment

**Greinox RP** for immediate development of the passive layer.

### Disposal

The product and the rinsing water must not be lead into the sewage system.

The product and the rinsing water must be disposed of according to legal requirements (hazardous waste).

Treatment in neutralisation plant or disposal by an authorised company is mandatory.

Local statutory regulations must be followed.

### Safety advice

The product contains hydrofluoric acid and nitric acid (C, corrosive, T, toxic).

Follow safety advice and instructions from EC safety data sheet.

### Declaration for transport

Corrosive liquid, toxic. not noted otherwise.

UN-No. 2922, class 8 (6.1) / PG II. ADR/RID

### Packing units

PE-can 2kg (in units of 6 cans at 2kg) Item-No.:03.6002